

OK Autrod 5356

OK Autrod 5356 is the most widely used welding alloy and can be classified as a general purpose type filler alloy. OK Autrod 5356 is typically chosen because of its relatively high shear strength. The 5XXX alloy base material, welded with OK Autrod 5356, with a weld pool chemistry greater than 3 % Mg and service temperatures in excess of 65 °C are susceptible to stress corrosion cracking. The alloy is non-heat treatable.

Specifiche	
Classificazioni	SFA/AWS A5.10 : ER5356 EN ISO 18273 : S Al 5356 (AlMg5Cr(A))
Omologazioni	ABS : WB ABS : ER 5356 BV : WB CE : EN 13479 CWB : ER5356 DB : 61.039.01 DNV : 5356 LR : WB/I-1 S RINA : WB RINA : WC (*) UKCA : EN 13479 VdTÜV : 04664

Le approvazioni si basano sulla posizione della fabbrica. Si prega di contattare ESAB per ulteriori informazioni.

Tipo di lega	AlMg 5
Gas di protezione	I1, I3 (EN ISO 14175)

Typical Wire Composition %							
Mn	Si	Cr	Al	Cu	Zn	Fe	Mg
0.13	0.05	0.12	94.560	0.01	0.01	0.13	4.9

Parametri di saldatura		
Amp	Diametro del filo	Volt
60-170 A	0.8 mm	13-24 V
90-275 A	1.0 mm	15-26 V
140-300 A	1.2 mm	20-29 V
190-350 A	1.6 mm	25-30 V
280-400 A	2.4 mm	26-31 V