

Classifications

EN ISO 14343-A	AWS A5.9 / SFA-5.9
G 19 12 3 L Si	ER316LSi

Characteristics and typical fields of application

Solid wire G 19 12 3 L Si / ER316LSi for joining and surfacing of matching and similar austenitic steels and cast steel grades. Good corrosion resistance. Max. service temperature 400°C.

Base materials

1.4401 X5CrNiMo17-12-2, 1.4404 X2CrNiMo17-12-2, 1.4409 GX2CrNiMo19-11-2, 1.4429 X2CrNiMoN17-12-3, 1.4432 X2CrNiMo17-12-3, 1.4435 X2CrNiMo18-14-3, 1.4436 X3CrNiMo17-12-3, 1.4571 X6CrNiMoTi17-12-2, 1.4580 X6CrNiMoNb17-12-2, 1.4583 X10CrNiMoNb18-12
UNS S31600, S31603, S31635, S31640, S31653
AISI 316L, 316Ti, 316Cb

Typical analysis

	C	Si	Mn	Cr	Ni	Mo
wt.-%	0.02	0.8	1.7	18.4	12.4	2.8

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength $R_{p0.2}$	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact energy ISO-V KV J	
	MPa	MPa	%	20°C	-196°C
u	430 (≥ 320)	580 (≥ 510)	38 (≥ 25)	120	45 (≥ 32)

u untreated, as-welded – shielding gas Ar + 2.5% CO₂

Operating data

Polarity	DC +	Dimension mm
Shielding gas (EN ISO 14175)	M12, M13	0.8
		1.0
		1.2
		1.6

Approvals

TÜV (19798), DB (43.132.93), CE